

## Selvol™ ULTALUX FA

Polyvinyl Alcohol

Sekisui Chemical Company, Ltd.

### Описание материалов:

SELVOL™ ULTALUX FA polyvinyl alcohol (PVOH) provides performance and functionality in face masks and peels, BB creams, anti-aging creams and lotions, deodorants/antiperspirants and scar treatment formulations. Ultalux FA offers a defined spectrum of performance attributes formulators require to manufacture select personal care products efficiently and effectively. As part of the Ultalux range of PVOH, the FA grade is tested for high quality and purity and is verified as non-irritating on skin.

### Главная Информация

Используется	Клеи
	Косметика

### Физический

Физический	Номинальное значение	Единица измерения
PH-4% водного раствора	4.5 to 6.5	
Вязкость раствора-15% водного раствора при 20 °C	5.1 to 5.7	Pa·s
Adhesion to Glass	80 to 120	g

### Механические

Механические	Номинальное значение	Единица измерения
Модуль растяжения <sup>1</sup>	11.0 to 13.8	MPa
Прочность на растяжение <sup>2</sup>	12.4 to 15.2	MPa
Удлинение при растяжении <sup>3</sup> (Break)	> 200	%

### NOTE

1.	Tensile properties and adhesion were measured on films containing 12% PVOH and 3% glycerin after casting and drying in a controlled temperature and humidity room for 24 hours
2.	Tensile properties and adhesion were measured on films containing 12% PVOH and 3% glycerin after casting and drying in a controlled temperature and humidity room for 24 hours
3.	Tensile properties and adhesion were measured on films containing 12% PVOH and 3% glycerin after casting and drying in a controlled temperature and humidity room for 24 hours

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

