

SABIC® PPcompound 8750MB2

Polypropylene

Saudi Basic Industries Corporation (SABIC)

Описание материалов:

SABIC® PPcompound 8750MB2 is a development grade, elastomer-modified Polypropylene for painted automotive exterior applications. When mixed together with 8750MB1 (in ration 60/40) the property profile of SABIC PPC 8750 (see datasheet 8750U) will be reached.

SABIC® PPcompound 8750MB2 is a designated automotive grade.

Главная Информация			
Добавка	Модификатор удара		
Характеристики	Модификация удара		
	Болезненный		
Используется	Автомобильные Приложения		
	Автомобильные внешние части		
Формы	Гранулы		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.905	g/cm ³	ISO 1183
Массовый расход расплава (MFR) (230°C/2.16 kg)	23	g/10 min	ISO 1133
Механические	Номинальное значение	Единица измерения	Метод испытания
Флекторный модуль ¹ (Injection Molded)	800	MPa	ISO 178
NOTE			

1. Type 1A

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

