

## BCC Resins BC 8001

Polyurethane

BCC Products Inc.

### Описание материалов:

BCC Kwik Kast/Black is a two component, fast setting polyurethane reproduction plastic. BC 8001 sets to a demoldable hardness within 30 minutes @ 77°F. Uses include; tracing models core boxes, duplicating aids, patterns, prototypes, low temperature vacuum form tools, etc.

#### Handling Properties:

BCC's Kwik Kast/Black is a fast-setting, two part casting system which requires careful preparation prior to mixing parts A and B. Because Kwik Kast/Black contains components of high density there will be some separation at the bottom of each container. Using a paint shaker, jiffy mixer, or mixing spatula, re-suspension of the ingredients is easily accomplished. Precaution should be taken to prevent any moisture contamination from containers or utensils. It is recommended that the work area be well ventilated and normal cleanliness and safety rules be observed. Avoid prolonged exposure to vapors and contact with skin.

#### Preparation of Mold Surface:

Clean the surface from dust and possible presence of moisture. Apply BC 87 Parting Agent and polish to a uniform high gloss finish (usually 2-3 coats are recommended). For plaster or wood surfaces seal with PVC sealer to ensure complete absence of moisture, followed by 2-3 coats of 87 Parting Agent.

#### Mixing and Pouring:

Although not necessary, best results are obtained by evacuation of each component under 29 inches of vacuum which removes entrapped air prior to blending the two components. Pour weighed or measured amounts of Part A & B into a separate dry container by pouring Part A into Part B. Mix with a spatula or mechanical stirrer for 30-40 seconds for quart size batches or 40-50 seconds for gallon batches while avoiding air entrapment. Immediately pour mixed resin uninterrupted from a convenient height above the mold cavity. Clean your mixing tools by rinsing in an alcohol type solvent. Larger masses (2 feet or more) may be built up with successive pours. Castings may be demolded within 30-60 minutes but should be properly supported while "green". Under normal conditions, maximum hardness or cure will be achieved in 12-18 hours.

Главная Информация			
Характеристики	<ul style="list-style-type: none"> <li>Быстрое лечение</li> <li>Хорошая стабильность размеров</li> <li>Низкий Exotherm</li> <li>Низкий и без запаха</li> <li>Низкая вязкость</li> </ul>		
Используется	<ul style="list-style-type: none"> <li>Моделирующий материал</li> <li>Прототипирование</li> </ul>		
Внешний вид	Черный		
Формы	Жидкость		
Метод обработки	Литье		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.66	g/cm <sup>3</sup>	ASTM D792
Формовочная усадка-Поток	0.080	%	ASTM D955
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore D)	85		ASTM D2240
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение (Break)	44.1	MPa	ASTM D638

Прочность на сжатие	62.7	МПа	ASTM D695
<b>Тепловой</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Температура отклонения при нагрузке (1.8 МПа, Unannealed)	80.6	°C	ASTM D648
<b>Термокомплект</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Компоненты термокомплекта			
Hardener	Mix Ratio by Weight: 1.0, Mix Ratio by Volume: 1.0		
Resin	Mix Ratio by Weight: 1.0, Mix Ratio by Volume: 1.0		
Срок службы горшка (24°C)	5.0 to 6.0	min	
Терморегулирующая вязкость	1500	cP	ASTM D2393
Время демолд (24°C)	30 to 45	min	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

