

King Pearl® E Series

Expanded Polystyrene

Loyal Chemical

Описание материалов:

King Pearl® E Series are high expansion materials for material saving applications.

Available variations:

E-MS: 1.0 - 1.6 mm particle size and 14 - 16 g/l foam density.

E-SA: 0.8 - 1.2 mm particle size and 16 - 18 g/l foam density.

E-SB: 0.6 - 0.9 mm particle size and 18 - 20 g/l foam density.

E-S: 0.4 - 0.7 mm particle size and 20 - 22 g/l foam density.

Главная Информация			
Используется	Упаковка		
Внешний вид	Доступные цвета		
Формы	Частицы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.02	g/cm ³	ASTM D792
Видимая плотность	0.60	g/cm ³	ASTM D1895

Дополнительная информация			
Blowing Agent: >6% PentaneResidual Monomer: <0.5%Moisture Content: <0.5%Aging Time after pre-expansion: 16 - 24 hrPre-expansion: Batch pre-expanderMain Steam Pressure: 4 - 5 kg/cm ² Chamber Pressure: 0.1 - 0.15 kg/cm ² Heating Time: 50 - 60 secKeeping Time: 10 secCooling Time: 40 - 50 secPre-expansion: Continuous pre-expanderMain Steam Pressure: 4 - 5 kg/cm ² Chamber Pressure: 0.15 - 0.3 kg/cm ² Chamber Temperature: 96 - 98°C			

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

