

## Baynat® 755 Polyol

Polyurethane

Covestro - PUR

### Описание материалов:

Baynat 755 Polyol is a polyether polyol mixture used when formulating urethane headliners. The system allows low weight, good thermal dimensional stability, and high definition of surface structure. As with any product, use of Baynat 755 Polyol in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

Главная Информация		
Используется	Автомобильные Приложения Детали интерьера автомобиля	
Формы	Жидкость	
Физический	Номинальное значение	Единица измерения
Удельный вес	1.02	g/cm <sup>3</sup>
Видимая плотность	1.02	g/cm <sup>3</sup>
Содержание воды	4.2 to 4.4	wt%
Точка вспышки-PMCC	122	°C
Hydroxyl Value	334 to 374	mg KOH/g

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

### Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

