

Maxxam™ FR PP Concentrate 4

Polypropylene

PolyOne Corporation

Описание материалов:

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings. MAXXAM FR PP Concentrate 4 is designed to impart good flame retardancy to polypropylene homopolymer as well as co-polymer. The letdown ratios will vary from one grade of polypropylene to another. When this concentrate is letdown at the proper ratio the resulting materials can achieve flame retardancy equivalent to the requirements of the UL-94 V-2 or VTM-2. Typical starting points for formulation range from 10-15% by weight PP Concentrate 4. Products manufactured with PP Concentrate 4 will be low or no bloom.

Главная Информация			
Характеристики	Огнестойкий Низкий цветение		
Формы	Гранулы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.32	g/cm ³	ASTM D792
Массовый расход расплава (MFR) ¹ (230°C/2.16 kg)	9.1 to 12	g/10 min	ASTM D1238
NOTE			
1.	Procedure A		

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

