

## PEARLSTICK® 46-10/16

Thermoplastic Polyurethane Elastomer (Polyester)

Lubrizol Advanced Materials, Inc.

### Описание материалов:

Pearlstick® 46-10/16 is an elastic, linear, aromatic polyurethane, supplied in form of white spherical granules with a very high crystallization rate and a high thermoplasticity level.

#### APPLICATIONS:

Pearlstick® 46-10/16 is used for the production of adhesives for plasticized PVC to plasticized PVC or other materials such as leather, textiles, metals, paper, etc. in the shoe and furniture industry. The addition of a polyfunctional isocyanate to improves the heat-resistance and the strength of the joints.

Главная Информация	
Характеристики	Ароматические
Используется	Текстильная склеивание
	Металлический пикап
	Клей
Внешний вид	Белый
Формы	Частицы

Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность (20°C)	1.19	g/cm <sup>3</sup>	ISO 2781
Вязкость <sup>1</sup> (20°C)	1.40 - 1.80	Pa·s	Internal method
Hydroxyl Value	0.10	%	Internal method
Температура активации	50	°C	EN 12961

Дополнительная информация	Номинальное значение	Единица измерения	Метод испытания
---------------------------	----------------------	-------------------	-----------------

SOLUBILITY: Pearlstick® 46-10/16 is soluble in Methylene chloride, Acetone, Methyl Ethyl Ketone (MEK), Ethyl Acetate and Tetrahydrofuran (THF). Diluting solvents such as Toluene can be added in large amounts. The solvents and diluents should be water-free (max. 0.1 %), so as to avoid subsequent side reactions during crosslinking with isocyanate. It should be dissolved in closed tanks, and the use of a variable speed agitator is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios

### NOTE

1. Brookfield RVF sp 4, 20 rpm.  
Solution at 15% in MEK

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

