

## Manner Flexible PVC V836

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

### Описание материалов:

Whether you need a flexible PVC or semi-rigid PVC for your wire and cable application, Manner Plastics has a material to meet your needs. We offer insulation and jacketing compounds in all standard operating ranges. The newest addition to our wire & cable family of materials is a compound which UL recognized for THWN-2 applications.

Our materials are used in a variety of applications including appliance, automotive, building, utility, and telecommunications.

The table below shows some of our most popular compounds, but is not a comprehensive view of the Manner Plastics product portfolio. If you do not see a compound offering the performance your application requires, please contact us. We may already have a custom formulation that meets your needs.

All Manner Plastics materials are RoHS compliant. Following is a representative sampling of our wire and cable compounds.

Главная Информация			
Характеристики	Хорошая гибкость		
Соответствие RoHS	Соответствует RoHS		
Формы	Гранулы		
Метод обработки	Экструзия		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.40	g/cm <sup>3</sup>	ASTM D792
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	80		ASTM D2240
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение (Yield)	19.2	MPa	ASTM D638
Удлинение при растяжении (Break)	470	%	ASTM D638
Старение	Номинальное значение	Единица измерения	
Изменение максимального удлинения в воздухе (100°C, 168 hr)	-7.0	%	
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура ломкости	-24.0	°C	ASTM D746
Воспламеняемость	Номинальное значение	Единица измерения	Метод испытания
Индекс кислорода	28	%	ASTM D2863
Дополнительная информация	Номинальное значение	Единица измерения	
Operating Temperature	80	°C	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

