

Baoding 6185B

Thermoplastic Polyurethane Elastomer

Baoding Bangtai Polymeric New-Materials Co.,Ltd

Описание материалов:

Properties: Hot melt adhesive film, especially has great bonding capacity with TPU, PVC, NYLON, leather, polyester and fabric. Excellent initial bonding strength, good solvent solubility, strong crystallization, low thermoplasticity, can be used as a mono-component adhesive or with a crosslinking agent. We can customize different viscosities for each grade.

Applications: Clothes, Shoes, Tents, Low-temp toe puff, Luggages, etc.

Главная Информация		
Характеристики	Bondability Хорошая адгезия	
Используется	Клеи Потребительские приложения Обувь Багаж	
Внешний вид	Прозрачный/прозрачный	
Физический	Номинальное значение	Единица измерения
Плотность	1.18 to 1.22	g/cm ³
Массовый расход расплава (MFR) (150°C/2.16 kg)	5.0 to 15	g/10 min
Твердость	Номинальное значение	Единица измерения
Твердость по суху (Shore A)	83 to 87	
Тепловой	Номинальное значение	Единица измерения
Температура плавления	115 to 125	°C

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

