

Tecnoflon® N 215

Fluoroelastomer

Solvay Specialty Polymers

Описание материалов:

Tecnoflon® N 215 is a very low viscosity fluoroelastomer copolymer. Tecnoflon® N 215 is intended for blending with other polymers of the Tecnoflon® family to achieve the desired viscosity. It is also intended for high concentration solution applications, such as dip coated items, fabric coatings and spray coating. Tecnoflon® N 215 can be mixed in the same way as all the other Tecnoflon® grades and can be used in any application requiring either very low compound viscosity or "low viscosity", highly loaded high hardness compounds. Tecnoflon® N 215 does not contain curatives: therefore the proper levels of Tecnoflon® FOR M1 and Tecnoflon® FOR M2 must be added to achieve the required properties. It can be also cured with diamine based systems such as Tecnoflon® Tecnocin A and Tecnoflon® Tecnocin B.

Some of the unique properties of Tecnoflon® N 215 are:

Solution applications

Excellent pot life

Very low Brookfield viscosity

Excellent adhesion to substrates

Dry applications

Superior mould flow

Low compound viscosity

Good compression set

Tecnoflon® N 215 can be mixed using typical fluoroelastomers compounding ingredients and mixing can be accomplished with two-roll mills or internal mixers.

Compounds based on Tecnoflon® N 215 can be dispersed in solvents for coating applications. Finished goods can be produced by a variety of rubber processing methods.

Главная Информация

Характеристики	Сополимер
	Хорошая адгезия
	Хороший поток
	Комплект низкого сжатия
	Низкая вязкость
Используется	Смешивание
	Нанесение покрытия
	Уплотнение
	Тканевые покрытия
Внешний вид	Полупрозрачный
Формы	Плита
Метод обработки	Покрытие
	Уплотнение
	Покрытие Dip
	Распыление

Физический

Номинальное значение

Единица измерения

Вязкость Mooney ¹ (ML 1+10, 121°C)	10	MU
Содержание фтора ²	66	%

NOTE

1. Raw polymer
2. Raw polymer

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat