

## Baydur® 728 IBS (35 pcf)

Polyurethane (MDI)

Covestro - PUR

### Описание материалов:

Baydur 728 IBS is a high-density polyurethane structural foam system used in the reaction injection molding (RIM) process. This system incorporates a specially engineered interactive blowing system (IBS) and internal mold release (IMR). The system is supplied as two reactive liquid components. Component A is a polymeric diphenylmethane diisocyanate (PMDI) and Component B is a formulated polyol system containing no CFC- or HCFC-blowing additives.

Baydur 728 IBS system is used in applications requiring a UL94 flammability rating of V-0 and/or 5VA for use in electronic, equipment housing, and appliance markets. The applications typically take advantage of the material's strength, excellent surface finish, and large-part capability. As with any product, use of the Baydur 728 IBS system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

Главная Информация			
UL YellowCard	E61384-475117	E61384-475574	
Добавка	Дующий агент Пресс-форма		
Характеристики	Хорошая прочность Хорошая поверхность		
Используется	Приборы Электрическое/электронное применение Корпуса		
Метод обработки	Литье под давлением реакции (обод)		
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение (Break, 6.35 mm)	13.1	MPa	ASTM D638
Удлинение при растяжении (Break, 6.35 mm)	8.0	%	ASTM D638
Флекторный модуль (6.35 mm)	814	MPa	ASTM D790
Flexural Strength (6.35 mm)	26.9	MPa	ASTM D790
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Charpy Unnotched Impact Strength <sup>1</sup>	13	kJ/m <sup>2</sup>	Internal Method
Зубчатый изод Impact (6.35 mm)	11	J/m	ASTM D256
Незубчатый изод Impact (6.35 mm)	110	J/m	ASTM D256
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура отклонения при нагрузке (0.45 MPa, Unannealed, 6.35 mm)	71.0	°C	ASTM D648
CLTE-Поток (70°C, 6.35 mm)	1.1E-4	cm/cm/°C	ASTM D696

## NOTE

1. 0.25 in

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

## Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

