

Lotryl® BESTPEEL 2012

Ethylene Methyl Acrylate Copolymer

Arkema

Описание материалов:

LOTRYL® BESTPEEL 2012 is a ready-to-use thermoplastic composition designed to make peelable heat seal layers onto various substrates. The base resin is a random copolymer of ethylene and methyl acrylate, polymerized by high-pressure process in autoclave reactor. Modification is introduced to ensure the best processability in the different film technologies, and the suitable properties in heat sealing and peeling.

Applications

LOTRYL® BESTPEEL 2012 is used as top layer of laminates in order to provide the functions of heat sealability onto various substrates like PP, PS, PET and PVC, and easy opening by interfacial peeling. In the case of transparent structures, it maintains high clarity with low haze.

LOTRYL® BESTPEEL 2012 is easily processed using the technologies of coextrusion coating, cast film coextrusion, blown film coextrusion or sheet coextrusion, to produce multilayers that can be used as lids, either directly or after lamination with other films.

Главная Информация			
Характеристики	Хорошее тепловое уплотнение Высокая четкость Случайный сополимер		
Используется	Пленка Ламинаты Крышки Уплотнения		
Метод обработки	Выдувная пленка Литая пленка Покрытие Созэкструдированная пленка Козэкструзия		
Физический	Номинальное значение	Единица измерения	Метод испытания
Массовый расход расплава (MFR) (190°C/2.16 kg)	12	g/10 min	ASTM D1238, ISO 1133
Содержание метилакрилата	18.0 to 22.0	wt%	
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура плавления	80.0	°C	ISO 11357-3
Оптический	Номинальное значение	Единица измерения	Метод испытания
Haze (50.0 µm)	10	%	ASTM D1003
Экструзия	Номинальное значение	Единица измерения	
Температура расплава	300 to 310	°C	

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

