

INEOS EMAA M28N430

Ethylene Methacrylic Acid

INEOS Olefins & Polymers Europe

Описание материалов:

Ethylene-MethAcrylic-Acid-Copolymer (EMAA) for extrusion coating.

Benefits & Features

M28N430 is an additive free ethylene-methacrylic-acid-copolymer (EMMA) with a high MAA content. Its special polymer structure gives the following properties:

Improved adhesion properties to standard LDPE/mLLDPE or other polar substrates, especially with aluminium foil and metallised film at high line speeds or low coating weights

Good processability in coextrusion with comparable neck in and draw down to LDPE

Exhibits very good sealing properties enhanced by the presence of the comonomer

Good organoleptical properties

Low fumes during processing an high purity

Applications

M28N430 is a speciality extrusion coating resin with improved adhesion characteristics. Main extrusion coating application for aluminium foil containing laminates in liquid food packaging and flexible packaging.

Главная Информация	
Характеристики	<p>Высокая чистота</p> <p>Не раздражающий газ</p> <p>Сополимер</p> <p>Обрабатываемость, хорошая</p> <p>Хорошие сенсорные характеристики</p> <p>Хорошее уплотнение тепла</p> <p>Хорошая адгезия</p> <p>Без добавления присадок</p>
Используется	<p>Покрyтия из фольги</p> <p>Упаковка</p> <p>Пищевая упаковка</p> <p>Нанесение покpытия</p>
Соответствие RoHS	Свяжитесь с производителем
Формы	Частицы
Метод обработки	<p>Кокстpузионное формование</p> <p>Экстpузионное покpытие</p>

Физический	Номинальное значение	Единица измерения	Метод испытания
Массовый расход расплава (MFR) (190°C/2.16 kg)	8.0	g/10 min	ISO 1133
Methacrylic Acid Content	8.3	%	Internal method

Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура плавления (DSC) ¹	101	°C	Internal method
Экструзия	Номинальное значение	Единица измерения	
Температура расплава	260 - 290	°C	
NOTE			
1.	10°C/min		

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

