

Sumiliteresin® PR-51649 BI

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-51649 BI is a straight novolak phenolic resin. It is generally apply for foundry.

Characteristics

SUMILITERESIN® PR-51649 BI is a flake phenolic resin with good properties in foundry manufacture. It is designed in High molecule number in order to get good anti-peel back of RCS. It is preferable add hexamine about 15%/resin when applied in resin coated sand (RCS).

Главная Информация		
Внешний вид	Белый Желтый	
Формы	Шелковистый	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	3.50 - 7.50	cm
Тепловой	Номинальное значение	Единица измерения
Температура плавления	65.0 - 85.0	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (150°C)	0.70 - 1.2	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

