

Andur 7003 AP-F

Polyurethane (Polyether, TDI)

Anderson Development Company

Описание материалов:

Andur 7003AP-F is a polyether (PPG) based liquid, toluene diisocyanate terminated prepolymer. A water-white clear elastomer with a hardness of 70 Shore A is obtained when this prepolymer is cured with Curene 89-LC. Elastomers of lower hardness can be obtained through the use of plasticizers.

Главная Информация			
Формы	Жидкость		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.04	g/cm ³	ASTM D792
Термокомплект	Номинальное значение	Единица измерения	Метод испытания
Терморегулирующая вязкость			ASTM D2393
21°C	6800	cP	ASTM D2393
70°C	400	cP	ASTM D2393

Дополнительная информация

NCO: 2.8 to 3.2% Specific Gravity, ASTM D792, 70°F: 1.04 g/ml Specific Gravity, ASTM D792, 212°F: 1.03 g/ml

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

