

## LUVOCOM® 1106-VAP-10

Углеродное волокно

Polyether Imide

Lehmann & Voss & Co.

### Описание материалов:

LUVOCOM®1106-VAP-10 is a polyetherimide (PEI) material, and the filler is carbon fiber reinforced material. This product is available in Europe.

LUVOCOM®The main features of 1106-VAP-10 are:

flame retardant/rated flame

Flame Retardant

Conductivity

High stiffness

high strength

LUVOCOM®The typical application fields of 1106-VAP-10 are: engineering/industrial accessories

Главная Информация			
Наполнитель/армирование	Армированный материал из углеродного волокна		
Характеристики	Проводящий Жесткий, высокий Высокая прочность Защита от электростатического разряда Хорошая мобильность Теплостойкость, высокая Огнестойкий		
Используется	Детали Насоса Втулка Шестерня Подшипник		
Внешний вид	Черный		
Физический	Номинальное значение	Единица измерения	Метод испытания
Формовочная усадка	0.050 - 0.20	%	DIN 16901
Поглощение воды (23°C, 24 hr)	< 0.20	%	
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения	28000	MPa	ISO 527-2
Tensile Stress (Break)	262	MPa	ISO 527-2
Растяжимое напряжение (Yield)	1.1	%	ISO 527-2
Флекторный модуль	25000	MPa	ISO 178
Флекторный стресс	385	MPa	ISO 178
Flexural Strain at Flexural Strength	1.5	%	ISO 178

Insulation Resistance		ohms	IEC 60167
<b>Воздействие</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Charpy Unnotched Impact Strength (23°C)	43	kJ/m <sup>2</sup>	ISO 179/1eU
<b>Электрический</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Удельное сопротивление поверхности	< 1.0E+3	ohms	IEC 60093
<b>Воспламеняемость</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Огнестойкость <sup>1</sup>	V-0		UL 94
<b>Интъекция</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	
Температура сушки			
Hot air dryer, A	120	°C	
Hot air dryer, B	150	°C	
Время сушки			
Hot air dryer, A	> 8.0	hr	
Hot air dryer, B	> 4.0	hr	
Рекомендуемая максимальная влажность	0.030	%	
Задняя температура	330 - 350	°C	
Средняя температура	340 - 390	°C	
Передняя температура	350 - 400	°C	
Температура сопла	350 - 400	°C	
Температура обработки (расплава)	380	°C	
Температура формы	150 - 180	°C	

## Инструкции по впрыску

### General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

### Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

### Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

### Additional Information

During processing the moisture level should not exceed 0.03%, otherwise porosity and surface defects (e.g. smearing) may occur. Predrying is recommended even when sealed original containers are being used. To avoid internal stresses, a low shear load should be used for processing.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

High-temperature polymers place increased demands on the tool steels employed.

Please contact us for further information.

## NOTE

1. Not recognized by UL.

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

