

Alpha PVC 3006-75

Flexible Polyvinyl Chloride

Mexichem Specialty Compounds Inc.

Описание материалов:

ALPHA PVC 3006-75 is a flexible vinyl compound produced with FDA sanctioned raw materials. Designed with high melt flow for injection molding, PVC 3006 features sparkling clarity, high thermal stability, and easy mold release. The formula is available in a wide range of hardnesses and preferred for such demanding applications as drip chambers, tubing caps and connectors, and respirator masks. Packaged as diced 1/8 inch cubes in 50 pound bags. Also available in Gaylords on special request.

Other Hardnesses: PVC 3006 is also available in 80, 85, 90, and 95, Shore A durometer. Alpha produces a full line of other compounds ranging from very soft, 40 durometer to full rigid.

PVC 3006 formulas bond easily with other flexible and rigid PVC parts by conventional solvent sealing (ketones) radio-frequency and heat sealing.

Packaging: Diced 1/8" cubes, 50 lb bags. Gaylords on special request.

Главная Информация			
Характеристики	<p>Высокая яркость</p> <p>Высокое разрешение</p> <p>Термическая стабильность, хорошая</p> <p>Хорошая производительность при потере</p>		
Используется	<p>Щит</p> <p>Соединитель</p>		
Рейтинг агентства	FDA не рассчитан		
Соответствие RoHS	Свяжитесь с производителем		
Внешний вид	<p>Доступные цвета</p> <p>Прозрачный/прозрачный</p>		
Формы	Куб		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.23	g/cm ³	ASTM D792
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра			ASTM D2240
Shaw A, 10 seconds, 3.18mm	75		ASTM D2240
Shaw A, 15 seconds, 6.35mm	73		ASTM D2240
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение			ASTM D638
Fracture	10.8	MPa	ASTM D638
100% strain	5.15	MPa	ASTM D638
Удлинение при растяжении (Break)	330	%	ASTM D638

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

