

## ELASTOSIL® R 570/70

Silicone

Wacker Chemie AG

### Описание материалов:

Silicone Rubber, HTV

Electrically Conductive Rolls, Printing Industry

Molded Parts, Technical, Plastics and Rubber Processing

Electrically Conductive Rollers, Printing Industry

Electrically Conductive Rollers, Plastics and Rubber Processing

Ignition and Battery Cables, Automotive & Transportation

Ignition and Battery Cables, Cable Industry

Instrumentation & Control Cables, Cable Industry

Главная Информация	
Характеристики	Проводящий Электропроводящий
Используется	Уплотнение Промышленное применение
Метод обработки	Прессформа сжатия Пресс-форма

Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Black		
Плотность	1.19	g/cm <sup>3</sup>	DIN 53479

Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	71		DIN 53505
Прочность на растяжение	6.40	MPa	DIN 53504
Удлинение при разрыве	160	%	DIN 53504
Комплект сжатия	29	%	DIN ISO 815-B
Tear Strength	13.0	kN/m	ASTM D624B
Сопrotивление громкости	3.6	ohms-cm	DIN IEC 93

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

**Susheng Import & Export Trading Co.,Ltd.**

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

