

BJB Polyurethane PC-10

Polyurethane Thermoset Elastomer

BJB Enterprises, Inc.

Описание материалов:

PC-10 is set up as a three component liquid material system. When added in increased amounts, the "C" component takes the basic A/B mixture from the texture of an ordinary soft gumdrop to a jelly-like consistency. One of the most unusual, yet, important features of this product is that regardless of the consistency, PC-10 can bounce back to its original shape. The maximum amount of "C" that can be added is 200% to a total A/B mixture. This level of "C" produces a gel that has a sticky, pressure-sensitive adhesive type surface. This can be a desirable feature as it can keep the gel in place when it is used to fill a bladder or bag.

PRODUCT HIGHLIGHTS:

Resists moisture absorption and is moisture insensitive during handling

Non-foaming

Does not contain MOCA, MDA or TDI

Non corrosive and compatible with electrical components

Very easy to use

Cures at room temperature

Главная Информация			
Характеристики	Хорошая адгезия Низкое поглощение влаги Неагрессивных		
Используется	Клеи		
Формы	Жидкость		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.948	g/cm ³	ASTM D792
Формовочная усадка-Поток	0.20	%	
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	13 to 17		ASTM D2240
Термокомплект	Номинальное значение	Единица измерения	Метод испытания
Компоненты термокомплекта			
Part A	Mix Ratio by Weight: 50		
Part B	Mix Ratio by Weight: 100		
Срок годности (25°C)	26	wk	
Терморегулирующая вязкость ¹ (25°C)	150	cP	ASTM D2393
Время демолд ² (25°C)	180	min	
Work Time ³ (25°C)	5.0 to 10.0	min	
Коэффициент смешивания-Часть C	200.0	wt%	
Водонепроницаемость ⁴ (25°C)	0.2	wt%	
NOTE			
1.	A/B		

2.	A/B
3.	A/B, 100g mass
4.	30 days

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

