

SI-LINK™ DFDA-5451 NT

Crosslinkable Polyethylene for Moisture Curable Power Cable Insulation

The Dow Chemical Company

Описание материалов:

SI-LINK™ Cross-linked polyethylene DFDA-5451 NT is an ethylene-silane copolymer used for power cables and control cables below 1 kV.

DFDA-5451 NT can be wet-induced crosslinking after the cable is extruded after adding DFDB-5480 NT catalyst masterbatch. If black cables are required for UV protection, it is recommended to add DFDB-5410 BK carbon black masterbatch.

Since the catalyst and carbon black masterbatch are transported separately with the DFDA-5451 NT copolymer, these components are very stable during the shelf life. The cross-linking reaction can only occur under the condition that the components are in contact with the wet content after melting and mixing.

specifications

when DFDB-5480 NT is used or DFDB-5410 BK is selected for cross-linking, products DFDA-5451 NT can generally meet the requirements of cables not higher than 1 kV in the following standards:

UL 854

ICEA:S-66-524

Canadian Standards Association (CSA) RW90

IEC:60502-1

Главная Информация			
Используется	Изоляция низкого напряжения Применение проводов и кабелей		
Рейтинг агентства	ICEA S-66-524 IEC 60502-1 UL 854		
Формы	Частицы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.922	g/cm ³	ASTM D792
Массовый расход расплава (MFR) (190°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение ¹	16.5	MPa	ASTM D638
Удлинение при растяжении ² (Break)	350	%	ASTM D638
Старение	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение-7 дней ³ (121°C)	90	%	ASTM D638
Коэффициент удлинения-7 дней ⁴ (121°C)	95	%	ASTM D638
Горячий ползет-15 мин, 20н/см ² ⁵ (150°C)		%	ICEA T-28-562
Горячий набор-15 мин, 0,2 МПа ⁶ (200°C)		%	IEC 60811-2-1

Электрический	Номинальное значение	Метод испытания
Диэлектрическая постоянная ⁷ (1 kHz)	2.30	ASTM D150
Коэффициент рассеивания ⁸ (60 Hz)	2.5E-4	ASTM D150

Дополнительная информация

Storage:

The environment or conditions of storage greatly influences the recommended storage time. Storage under extreme conditions may affect the quality, processing, or performance of the product. Storage should be in accordance with good manufacturing practices. The recommended storage conditions are dry conditions with temperatures between 50°F and 86°F (10°C and 30°C). When stored under these conditions, the product may be used by the customer for up to one year from the date of sale or two years from the date of manufacture, whichever comes first. It is recommended that the practice of using the product on a first-in / first-out basis be established.

Экструзия	Номинальное значение	Единица измерения
Температура сушки	60.0 - 71.1	°C
Время сушки	4.0 - 6.0	hr
Температура расплава	149 - 232	°C

Инструкции по экструзии

DFDA-5451 NT will extrude with excellent surface quality and without extrusion scorch if the accompanying catalyst masterbatch, DFDB-5480 NT and the carbon black masterbatch, DFDB-5410 BK, are kept dry. It is especially recommended that the catalyst and carbon masterbatches be dried at 140°F-160°F (60°-70°C) for four to six hours using dehumidified air prior to mixing and extrusion. Melt temperatures in the range of 300°F-450°F (150-230°C) have been successfully used. After extrusion of the appropriate mixture of this product and its catalyst and carbon black masterbatches, cross-linking can be achieved by allowing moisture to diffuse into the product. Most fabricators find that a hot water bath or sauna works best. To achieve a hot creep elongation of 100%, the typical times shown below are required (45 mil [1.1 mm] wall on 14 AWG [2.1 mm²] wire).

70°C: 10 hrs

90°C: 3.5 hrs

Specific recommendations for your particular equipment and conditions can be determined by contacting your local Dow Wire and Cable sales representative.

NOTE

1.	Crosslinked polyethylene properties (95% DFDA-5451 NT, 5% DFDB-5480 NT)
2.	Crosslinked polyethylene properties (95% DFDA-5451 NT, 5% DFDB-5480 NT)
3.	Crosslinked polyethylene properties (95% DFDA-5451 NT, 5% DFDB-5480 NT)
4.	Crosslinked polyethylene properties (95% DFDA-5451 NT, 5% DFDB-5480 NT)
5.	Measured on 14 AWG (2.1 mm ²) wire with a 30 mil (0.75 mm) wall after 4 hours curing in 90°C water. Crosslinked polyethylene properties (95% DFDA-5451 NT, 5% DFDB-5480 NT)
6.	Measured on 14 AWG (2.1 mm ²) wire with a 30 mil (0.75 mm) wall after 4 hours curing in 90°C water. Crosslinked polyethylene properties (95% DFDA-5451 NT, 5% DFDB-5480 NT)

7. Crosslinked polyethylene
properties (95% DFDA-5451 NT,
5% DFDB-5480 NT)

8. Crosslinked polyethylene
properties (95% DFDA-5451 NT,
5% DFDB-5480 NT)

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

