

## LUVOCOM® 1-8260

Стекловолокно

Polyamide 66

Lehmann & Voss & Co.

### Описание материалов:

LUVOCOM®1-8260 is a polyamide 66 (nylon 66) material, which contains a glass fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 1-8260 are:

Conductivity

Good stiffness

heat stabilizer

Typical application areas include:

Electrical/electronic applications

Reflector

House

textile/fiber

engineering/industrial accessories

Главная Информация			
Наполнитель/армирование	Армированный стекловолокном материал		
Добавка	Стабилизатор тепла		
Характеристики	Теплопроводность		
	Жесткий, хороший		
	Хорошая прочность		
	Термическая стабильность		
Используется	Зеркало		
	Текстильные изделия		
	Инженерные аксессуары		
	Переключатель		
	Применение в автомобильной области		
	Бизнес-оборудование		
	Чехол		
Катушка			
Внешний вид	Серый		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.64	g/cm <sup>3</sup>	ISO 1183
Формовочная усадка	0.20 - 0.50	%	DIN 16901
Поглощение воды (23°C, 24 hr)	< 1.0	%	
Механические	Номинальное значение	Единица измерения	Метод испытания

Модуль растяжения	12000	MPa	ISO 527-2
Tensile Stress (Break)	125	MPa	ISO 527-2
Растяжимое напряжение (Yield)	1.4	%	ISO 527-2
Флекторный модуль	10000	MPa	ISO 178
Флекторный стресс	180	MPa	ISO 178
Flexural Strain at Flexural Strength	1.8	%	ISO 178
Максимальная рабочая температура-Короткий срок	160	°C	
Insulation Resistance	> 1.0E+12	ohms	IEC 60167
<b>Воздействие</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Charpy Unnotched Impact Strength (23°C)	25	kJ/m <sup>2</sup>	ISO 179/1eU
<b>Тепловой</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Температура непрерывного использования	120	°C	UL 746B
Теплопроводность <sup>1</sup>	2.2	W/m/K	
<b>Электрический</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	<b>Метод испытания</b>
Удельное сопротивление поверхности	> 1.0E+12	ohms	IEC 60093
<b>Иньекция</b>	<b>Номинальное значение</b>	<b>Единица измерения</b>	
Температура сушки			
Hot air dryer, A	75.0	°C	
Vacuum dryer, B	105	°C	
Время сушки			
Hot air dryer, A	6.0 - 16	hr	
Vacuum dryer, B	4.0 - 6.0	hr	
Рекомендуемая максимальная влажность	0.10	%	
Задняя температура	290 - 310	°C	
Средняя температура	290 - 310	°C	
Передняя температура	290 - 310	°C	
Температура сопла	280 - 300	°C	
Температура обработки (расплава)	290	°C	
Температура формы	90.0 - 120	°C	
<b>Инструкции по впрыску</b>			

## General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

## Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

## Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

## Additional Information

During processing the moisture level should not exceed 0.1%, otherwise molecular degradation and surface defects (e.g. smearing) may occur. Due to rapid absorption of water, originally sealed containers should only be opened immediately prior to processing. Excessively high predrying temperatures may cause discoloration.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

## NOTE

1. Hot-Disk, 60x60x3 mm

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

## Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

