

Braskem PP C123-01N

Polypropylene Impact Copolymer

Braskem Europe GmbH

Описание материалов:

Braskem C123-01N Polypropylene Resin is a high performance impact copolymer developed for extrusion and blow moulding applications. Braskem C123-01N Polypropylene Resin is a high stiffness, high impact copolymer offering an excellent combination of high stiffness and toughness with good processability. Braskem C123-01N Polypropylene Resin is nucleated and features very high crystallization temperature.

Applications for Braskem C123-01N Polypropylene Resin:

Sheet
Blow moulding
Extrusion profiles
Thermoforming
Regulatory Information

Braskem C123-01N Polypropylene Resin should comply with EU, No 10/2011. It is the responsibility of the manufacturers of food contact articles and industrial food packers to make sure the articles in their actual use are in compliance with the imposed migration requirements. The appropriate regulations should be consulted for more detailed information. Compliance letters can be obtained through the Braskem sales representative.

Главная Информация			
Рейтинг агентства	ЕС без 10/2011		
Формы	Гранулы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.900	g/cm ³	ISO 1183
Массовый расход расплава (MFR) (230°C/2.16 kg)	1.3	g/10 min	ISO 1133
Механические	Номинальное значение	Единица измерения	Метод испытания
Tensile Stress (Yield, Injection Molded)	27.0	MPa	ISO 527-2
Растяжимое напряжение (Yield, Injection Molded)	7.0	%	ISO 527-2
Флекторный модуль (Injection Molded)	1450	MPa	ISO 178
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Ударная прочность			ISO 179/1eA
-20°C, Injection Molded	8.0	kJ/m ²	
0°C, Injection Molded	12	kJ/m ²	
23°C, Injection Molded	55	kJ/m ²	
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Heat Deflection Temperature ¹ (0.45 MPa, Unannealed)	95.0	°C	ISO 75-2/B
Викат Температура размягчения ²	151	°C	ISO 306/A

NOTE	
1.	Injection Molded
2.	Injection Molded

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

