

CONTINUUM™ DGDA-2492 BK

Bimodal Polyethylene Resin

The Dow Chemical Company

Описание материалов:

CONTINUUM™ DGDA-2492 BK Bimodal Polyethylene Resin is produced using UNIPOL™ II process technology. This product may be utilized for pipe applications where long-term hydrostatic strength combined with outstanding resistance to slow crack growth, rapid crack propagation, and high melt strength is desired. Suitable applications include natural gas distribution pipes, large diameter industrial piping, mining, sewage, and municipal water service lines.

Industrial Standards Compliance:

ASTM D 3350: cell classification

Black - PE445576C (MRS) (See notes 1)

Black - PE445574C (HDB) (See notes 1)

Plastics Pipe Institute (PPI): TR-4

Black Pipe - CONTINUUM™ DGDA-2492 BK (See Notes 1)

ISO PE100 pipe grade - MRS 10 @ 20°C; CRS 6.3 @ 60°C, 11 yr

ASTM PE4710 pipe grade - 1600psi HDB and 1000psi HDS @ 73°F, 1000psi HDB @ 140°F

NSF International: Standard 14 and 61

Black Pipe - DGDA-2492 BK³

ASME

Code Case N755

Consult the regulations for complete details.

Notes:

(1) Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

Главная Информация			
Добавка	Обработка помощи		
Рейтинг агентства	Астм д 3350 PE445574C Астм д 3350 PE445576C ASTM PE4710 ISO PE 100 Утверждено NSF 14 Утверждено NSF 61 PPI TR-4		
Формы	Гранулы		
Метод обработки	Экструзионный профиль		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность			ASTM D1505
Natural	0.949	g/cm ³	
Black ¹	0.959	g/cm ³	
Массовый расход расплава (MFR)			ASTM D1238
190°C/2.16 kg	0.060	g/10 min	
190°C/21.6 kg	6.5	g/10 min	

Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение ² (Yield)	> 24.1	MPa	ASTM D638
Удлинение при растяжении ³ (Break)	> 500	%	ASTM D638
Флекторный модуль	1030	MPa	ASTM D790B
Прочность на разрыв-1798 фунтов/кв. дюйм (12,4 МПа)(20 °C)	> 200	hr	ISO 1167
Гидростатическая прочность			ASTM D1598
1798 psi (12.4 MPa) : 20°C	> 100	hr	
725 psi (5.0 MPa) : 80°C	> 1000	hr	
Устойчивость к быстрому размножению трещин, ПК ⁴			
Calculated, Full Scale (@32°F) : 0°C	> 46.0	bar	ISO 13478
S-4 (@32°F) : -18°C	> 12.0	bar	ISO 13477
Устойчивость к быстрому размножению трещин, Тс-S-4 Тс (@ 12 бар) ⁵	< -18	°C	ISO 13477
Медленная трещина роста ⁶	> 10000	hr	ASTM F1473
Термическая стабильность	> 220	°C	ASTM D3350
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Зубчатый изод Impact ⁷ (23°C)	490	J/m	ASTM D256A
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура ломкости	< -75.0	°C	ASTM D7426

NOTE

- Natural resin extruded under proper conditions with carbon black masterbatch DFNF-0092 (6.5%).
- Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.
- Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.
- Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11.
- Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11.

6. Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

7. Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

