

## SILVER® RV-90/3-K

Polyvinyl Chloride

Guangdong Silver Age Sci & Tech. Co., Ltd

### Описание материалов:

SILVER® PVC for Wire and Cable is produced based on high quality PVC resin by adding modified additives. The modified plastic entirely conforming to RoHS is of excellent mechanical and processing properties. In addition, the custom-made products should be developed by buyers' requirements in order to meet special usage.

| Главная Информация            |                               |                   |
|-------------------------------|-------------------------------|-------------------|
| Добавка                       | Неуказанная добавка           |                   |
| Используется                  | Применение проводов и кабелей |                   |
| Соответствие RoHS             | Соответствует RoHS            |                   |
| Физический                    | Номинальное значение          | Единица измерения |
| Удельный вес                  | 1.41 to 1.45                  | g/cm <sup>3</sup> |
| Твердость                     | Номинальное значение          | Единица измерения |
| Твердость дюрометра (Shore A) | 85 to 89                      |                   |
| Механические                  | Номинальное значение          | Единица измерения |
| Прочность на растяжение       |                               |                   |
| -- <sup>1</sup>               | > 18.0                        | MPa               |
| --                            | > 17.0                        | MPa               |
| Удлинение при растяжении      |                               |                   |
| Break <sup>2</sup>            | > 170                         | %                 |
| Break                         | > 180                         | %                 |
| Дополнительная информация     | Номинальное значение          | Единица измерения |
| Temperature Resistance        | 90.0                          | °C                |
| NOTE                          |                               |                   |
| 1.                            | after aging (135°C/240h)      |                   |
| 2.                            | after aging (135°C/240h)      |                   |

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

