

## FM® 300-2

Adhesive

Cytec Industries Inc.

### Описание материалов:

FM® 300-2 film adhesive is a 250°F (121°C) cure version of Cytec Engineered Materials' widely used FM® 300 film adhesive. It delivers the same superior high temperature performance, toughness and stress/strain properties of FM 300 film adhesive without requiring a 350°F (177°C) cure cycle. In addition, FM 300-2 film adhesive's processing window includes temperatures up to 300°F (149°C) providing a unique level of flexibility from one adhesive product. FM 300-2 adhesive was developed specifically for co-cure and secondary composite bonding applications. Through innovative curative technology, the required cure temperature is reduced allowing for secondary bonding of structure far below the composite's glass transition point. FM 300-2 film adhesive also offers optimum flow control desirable for co-cure composite bonding. In metal bond applications, FM 300-2 film adhesive provides excellent moisture and corrosion resistance in high humidity environments with a minimal reduction in mechanical properties. To achieve consistent mechanical performance as well as maximum environmental resistance in bonding metallic details, the use of pre-cured BR® 127 corrosion inhibiting primer is recommended. FM 300-2 adhesive is available as an unsupported or supported film employing both knit and random mat carriers. A low-flow version of FM 300-2 film adhesive for composite interleaving, designated FM 300-2 interleaf adhesive, is also available.

#### Suggested Applications:

Co-cure and secondary composite bonding

Vacuum-only processing common in repair applications

Главная Информация		
Характеристики	Хорошая адгезия	
	Хорошая коррозионная стойкость	
	Хорошая прочность	
	Высокая термостойкость	
	Устойчивость к влажности	
Используется	Клеи	
	Склеивание	
Внешний вид	Красный	
Формы	Пленка	
Дополнительная информация	Номинальное значение	Единица измерения
Испарители	< 1.0	%

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

### Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

