

## BJB Polyurethane SC-92

Polyurethane Thermoset Elastomer

BJB Enterprises, Inc.

### Описание материалов:

SC-92 is a water-based, aliphatic polyurethane coating designed to provide a final finish or paintable surface for various flexible polyurethane foams, elastomers, and latex products. It can also be used as an in-mold coating for casting or brushing polyurethane products behind.

#### Product Highlights:

Provides a uniform semi-gloss finish

Clear base is easy to tint or pigment

Excellent color retention

High elongation and tear resistance

Главная Информация			
Характеристики	<p>Глянцевый, средний</p> <p>Распылитель</p> <p>Хорошая прочность на разрыв</p> <p>Хорошая стабильность цвета</p> <p>Хорошая окраска</p> <p>Увеличенная скорость растяжения</p> <p>Алифатический</p>		
Используется	Нанесение покрытия		
Внешний вид	Прозрачный/прозрачный		
Метод обработки	Покрытие		
Физический	Номинальное значение	Единица измерения	
Удельный вес	1.03	g/cm <sup>3</sup>	
Содержание ЛОС	10.0	kg/m <sup>3</sup>	
Содержание твердых веществ	45	%	
Вязкость (25°C)	125	mPa·s	
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Tensile Stress			
100% strain	3.31	MPa	
200% strain	4.69	MPa	
300% strain	6.14	MPa	
Прочность на растяжение (Yield)	27.6	MPa	ASTM D412
Удлинение при растяжении (Break)	750	%	ASTM D412
Термокомплект	Номинальное значение	Единица измерения	
Срок годности	52	wk	
Дополнительная информация			

The recommended method of applying SC-92 is by spraying with conventional spray gun. Brush coats may be used but spraying is more uniform. The recommended spray pressures with a conventional spray gun will normally range between 15 to 25 psi. When pigmented with BJB's 7100 Series water based pigments, 2 to 3 coats should be applied to achieve an opaque film. Surfaces should be clean and dry. A liquid dish soap and water solution is an effective surface cleaner. A primer like BJB's TC-89 will greatly increase adhesion to surface.

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

