

MonoSol® F300

Cellulose Acetate

MonoSol, LLC

Описание материалов:

MonoSol F300 is cellulosic-based edible water-soluble film manufactured using MonoSol's proprietary solution cast technology. MonoSol F300 is engineered for water-soluble barrier film and packaging applications. Made from edible cellulosic polymers, this film is designed to be converted on conventional packaging machines. The standard thickness is 50 microns (2.0 mil).

Главная Информация			
Характеристики	Барьерная смола		
	Биоразлагаемый		
	Съедобные		
	Водорастворимый		
Используется	Пленка		
	Упаковка		
Формы	Пленка		
Физический	Номинальное значение	Единица измерения	Метод испытания
Растворимость			Internal Method
Disintegration : 10°C, 50.8 µm	10.0	sec	
Dissolution : 10°C, 50.8 µm	40.0	sec	
Пленки	Номинальное значение	Единица измерения	Метод испытания
Толщина пленки протестирована	51	µm	
Толщина пленки-рекомендовано/доступно	50 µm		
Прочность на растяжение-MD (Break, 51 µm)	38.6	MPa	ASTM D882
Растяжимое удлинение-MD (Break, 51 µm)	35	%	ASTM D882

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

