

Fluon® PTFE RB1025S

25% стекловолокно

Polytetrafluoroethylene

Asahi Glass Co., Ltd.

Описание материалов:

Fluon®PTFE FC has improved creep and wear resistance. A wide range of fillers such as glass fiber, graphite, bronze, carbon fiber are available. Properties of each grades are listed later in tables.

Applications:

bearing
gasket
valvedisk
V-ring
O-ring
plug
valve
sheet
pump
impeller
mechanical seal

Characteristics:

improved wear resistance.
improved compression resistance
filler can be damaged by strong base and hydrogen fluoride
improved power flow for Z-type of PA

Главная Информация		
Наполнитель/армирование	Стекловолокно, 25% наполнитель по весу	
Характеристики	Хороший поток	
Используется	Подшипники	
	Прокладки	
	Вилки	
	Детали Насоса	
	Уплотнения	
	Лист	
	Клапаны/Детали Клапана	
Формы	Порошок	
Физический	Номинальное значение	Единица измерения
Удельный вес		
--	2.22	g/cm ³
--	0.530	g/cm ³
Механические	Номинальное значение	Единица измерения
Прочность на растяжение	20.6	МПа
Удлинение при растяжении (Break)	270	%

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

