

LUVOCOM® 1105-7786 VP

Polyetheretherketone

Lehmann & Voss & Co.

Описание материалов:

LUVOCOM®1105-7786 VP is a polyetheretherketone (PEEK) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main characteristics of 1105-7786 VP are:

flame retardant/rated flame

Flame Retardant

anti-warping

chemical resistance

Wear-resistant

Typical application areas include:

engineering/industrial accessories

textile/fiber

Aerospace

Automotive Industry

Handle

Главная Информация			
Добавка	Ptfe лубрикант		
Характеристики	Низкий уровень защиты		
	Хорошая химическая стойкость		
	Хорошая стойкость к истиранию		
	Сопротивление гидролизу		
	Смазка		
Используется	Огнестойкий		
	Ручка		
	Текстильные изделия		
	Инженерные аксессуары		
	Аэрокосмическое применение		
	Машина/механические детали		
Внешний вид	Применение в автомобильной области		
	Медицинские принадлежности/принадлежности для ухода		
	Подшипник		
Черный			
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.35	g/cm ³	ISO 1183
Плавкий объем-расход (MVR) (380°C/10.0 kg)	16.0	cm ³ /10min	ISO 1133

Формовочная усадка	1.0 - 1.8	%	DIN 16901
Поглощение воды (23°C, 24 hr)	< 0.050	%	
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения	3600	MPa	ISO 527-2
Tensile Stress (Break)	90.0	MPa	ISO 527-2
Растяжимое напряжение (Yield)	5.0	%	ISO 527-2
Флекторный модуль	3000	MPa	ISO 178
Флекторный стресс	130	MPa	ISO 178
Flexural Strain at Flexural Strength	6.5	%	ISO 178
Максимальная рабочая температура-Короткий срок	260	°C	
Insulation Resistance	> 1.0E+12	ohms	IEC 60167
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Ударная прочность (23°C)	5.0	kJ/m ²	ISO 179/1eA
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура непрерывного использования	250	°C	UL 746B
Воспламеняемость	Номинальное значение	Единица измерения	Метод испытания
Огнестойкость ¹	V-0		UL 94
Иньекция	Номинальное значение	Единица измерения	
Температура сушки			
Hot air dryer, A	150	°C	
Hot air dryer, B	120	°C	
Время сушки			
Hot air dryer, A	3.0 - 6.0	hr	
Hot air dryer, B	6.0 - 8.0	hr	
Рекомендуемая максимальная влажность	0.050	%	
Задняя температура	360 - 370	°C	
Средняя температура	380 - 390	°C	
Передняя температура	390 - 400	°C	
Температура сопла	360 - 380	°C	
Температура обработки (расплава)	390	°C	
Температура формы	170 - 190	°C	
Инструкции по впрыску			

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing, the moisture content should not exceed 0.05%. To avoid internal stresses, a medium to high injection rate should be used. An increase in tool temperature may be helpful. Post-crystallization may lead to warpage at elevated operating temperatures. This can be counteracted by suitable heat treatment.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

High-temperature polymers place increased demands on the tool steels employed.

Please contact us for further information.

NOTE

1. Not recognized by UL.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

