

SILVER® PP 423G30

30% стекловолокно

Polypropylene

Guangdong Silver Age Sci & Tech. Co., Ltd

Описание материалов:

SILVER® Modified Polyolefin includes modified polyethylene and modified polypropylene. Modified polyethylene is mainly applied to cable jacket. Black polyethylene compound is composed of polyethylene resin, carbon black, antioxidant and so on. Black polyethylene compound is applied to communication cable, control cable, signal cable, power cable, optical cable and submarine cable. It conforms to GB15065-94 Standard. Modified PP including flame resistant, glass fiber and mineral reinforced and weather-resistant, is widely applied in electronic & electrical appliances, household appliances, auto accessories, lightings, mechanical components and sockets, and so on. In addition, we develop new products according to customer's specific requirements.

Flame retardant PP

Characteristics:

glass fiber reinforced PP

Applications:

household appliance accessory, washer and other mechanical parts inner mechanical parts

Главная Информация			
Наполнитель/армирование	Стекловолокно, 30% наполнитель по весу		
Используется	Компоненты прибора		
	Машина/механические детали		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.14	g/cm ³	ASTM D792
Массовый расход расплава (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение ¹	75.0	MPa	ASTM D638
Удлинение при растяжении ² (Break)	4.0	%	ASTM D638
Флекторный модуль ³	5500	MPa	ASTM D790
Flexural Strength ⁴	110	MPa	ASTM D790
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Зубчатый изод удара (площадь) (23°C)	9.00	kJ/m ²	ASTM D256
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура отклонения при нагрузке (1.8 MPa, Unannealed)	150	°C	ASTM D648
NOTE			
1.	10 mm/min		
2.	10 mm/min		
3.	5.4 mm/min		
4.	5.4 mm/min		

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

