

ELASTOSIL® RT 713

Silicone

Wacker Chemie AG

Описание материалов:

Silicone Rubber, RTV-2

Bonding & Sealing, Adhesives and Sealants

Bonding & Sealing, Renewable Energies

Elect. Control Devices/Protect Sensors, Electronics

Elect. Control Devices/Protect Sensors, Automotive & Transportation

Electronic Control Devices, Electrical Industry

Electronic Control Devices, Automotive & Transportation

Electronic Control Devices, Electronics

Главная Информация

Используется	Клеи
	Склеивание
	Герметики

Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Grey		
Плотность			
--	0.750	g/cm ³	ISO 2781
--	0.750	g/cm ³	DIN 53479
Вязкость			
--	80	Pa·s	
--	80	Pa·s	ISO 3219
Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	23		ISO 868
Прочность на растяжение	1.50	MPa	ISO 37
Удлинение при разрыве	350	%	ISO 37
Tear Strength	7.00	kN/m	ASTM D624B

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

