

SOLPLAST TH 8000B

Styrene Ethylene Butylene Styrene Block Copolymer + SBS

UTEKSOL d.o.o.

Описание материалов:

Is a commercial name for thermoplastic elastomers (TPE - S) based on SBS, SEBS (styrene - butadiene - styrene; styrene - ethylene butadiene - styrene) block copolymers, gathered with mixing SBS, SEBS, ... elastomers with polyolefines such as PP, PE, EVA, ...

Resistance to acid, bases and all aqueous solutions is excellent.

Resistance to alcohol and glycols is medium good.

Resistance to aromatic hydrocarbons, fat and of oil is bad.

Resistance round series upwards loosely increases.

All "SOLPLASTS" have a good electric-volume resistance: that's more then 1e12 ohm-cm.

For coloring masters are used on a polyolefine base (PE, PP, EVA).

SERIES 8000

Technical compaund on SBS + SEBS block copolymers base;

Different phisical characteristics and optics considering purpose of use.

Work temperature between - 50 in + 60°C, very shortly up to +80°C

For aplication with higher coloral stability of the product under light exposure.

Approved stability to higher temperatures at shorttime loads.

8000B

Injection moulded project

Washers for pipes

| Главная Информация | | | |
|--------------------------------|--|-------------------|-----------------|
| Характеристики | Кислотоупорный Устойчивость к основанию Хорошая стабильность цвета | | |
| Используется | Шайба | | |
| Метод обработки | Литье под давлением | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Плотность | 1.04 to 1.16 | g/cm ³ | ISO 1183 |
| Массовый расход расплава (MFR) | 10 to 20 | g/10 min | ISO 1133 |
| Твердость | Номинальное значение | Единица измерения | Метод испытания |
| Твердость по суше (Shore A) | 45 to 65 | | ISO 868 |
| Эластомеры | Номинальное значение | Единица измерения | Метод испытания |
| Комплект сжатия (72°C, 23 hr) | 60 to 70 | % | ISO 815 |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

