

## SUPRENE® 537-2

Ethylene Propylene Diene Terpolymer

SK Global Chemical

### Описание материалов:

SUPRENE EPDM 537-2 is used by blending with IIR.

SUPRENE EPDM 537-2 shows excellent heat aging properties, especially with peroxide cures. It blends easily in all formulation and gives excellent weathering and low temperature impact properties.

SUPRENE EPDM 537-2 is mainly used in blends with IIR for inner tubes. It can also be used in various applications such as mechanical goods.

Главная Информация			
Характеристики	Хорошая термостойкость к старению Хорошая устойчивость к погоде Ударопрочность при низкой температуре		
Используется	Смешивание Машина/механические детали Трубка		
Формы	Тюк		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.860	g/cm <sup>3</sup>	ASTM D792
Вязкость Mooney (ML 1+4, 125°C)	40	MU	ASTM D1646
Ethylene Content	57.0	wt%	ASTM D3900
Содержание этилидена норборнена (ENB)	3.0	wt%	ASTM D6047
Летучее вещество	0.30	wt%	ASTM D5668

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat