

Varcum 29112

Phenolic

Durez Corporation

Описание материалов:

Varcum 29111 is used for applications involving critical taste considerations.

For use in metal coating formulations.

Exhibits sufficient flexibility without the addition of modifiers.

Plasticizers can be utilized where maximum flexibility is required.

Solvency characteristics permit the use of reasonable amounts of hydrocarbon solvents.

Blends of alcohols and/or ketones with hydrocarbons are recommended. Such blends should be formulated from alcohols, ketones, and hydrocarbons having uniform evaporation rates in order not to disturb the solvent blend ratio during the drying of coating film. A percentage of a high boiling alcohol or ketone is therefore recommended to prevent phase separation during the drying process. In can coating applications requiring maximum flexibility, the use of plasticizing modifiers, such as vinyl or epoxy resins, is recommended. Can coating formulations containing 4-8% of vinyl resin modifier will generally meet the most extreme requirements.

Главная Информация			
Характеристики	Хорошая гибкость		
Используется	Нанесение покрытия		
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Softening Point ¹	68	°C	Internal Method
Термокомплект	Номинальное значение	Единица измерения	Метод испытания
Терморегулирующая вязкость (25°C)	288	cP	Internal Method
Время доставки (150°C)	0.032	hr	
NOTE			
1.	cap. shrink		

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat