

OnForce™ LFT LF5200-5003 NATURAL

Длинное стекловолокно

Polypropylene

PolyOne Corporation

Описание материалов:

PolyOne's Long Fiber Thermoplastic (LFT) compounds are formulated for demanding applications which require high stiffness and good impact such as metal replacement or other structural applications. These products exhibit enhanced physical and mechanical properties versus standard short fiber products. Benefits of LFT compounds include improved impact strength, elastic modulus, and material strength across wide temperature ranges from subambient to highly elevated. Furthermore, LFT compounds have been shown to offer improved performance in the areas of creep and fatigue performance, improved dimensional stability, and exhibit an exceptional surface finish when compared to traditional highly filled short fiber products.

Главная Информация			
Наполнитель/армирование	Длинное стекловолокно		
Формы	Частицы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.28	g/cm ³	ISO 1183
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения	11000	MPa	ISO 527-2
Tensile Stress (Break)	130	MPa	ISO 527-2
Растяжимое напряжение (Break)	1.7	%	ISO 527-2
Флекторный модуль	8900	MPa	ISO 178
Флекторный стресс	190	MPa	ISO 178
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Ударная прочность	26	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	78	kJ/m ²	ISO 179
Ударное падение Dart	123	J	ASTM D5420
Инъекция	Номинальное значение	Единица измерения	
Температура сушки	80.0	°C	
Время сушки	2.0	hr	
Температура обработки (расплава)	210 - 230	°C	
Температура формы	60.0	°C	
Скорость впрыска	Slow-Moderate		
Back Pressure	1.00	MPa	

Инструкции по впрыску

LFT compounds can be processed using equipment similar to that used for short fiber products. The mechanical properties of finished parts depend greatly on the length of the fibers in the molded part; therefore processing conditions must be set carefully in order to minimize fiber breakage. A "low shear process" is advised, with low back pressure, low screw speed and low-to-medium injection speed.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

