

Algoflon® D 1610 F

Polytetrafluoroethylene

Solvay Specialty Polymers

Описание материалов:

Algoflon® D 1610 F is a PFOA-free white aqueous PTFE dispersion. It is designed for additivation of plastics and is particularly recommended for use as anti-drip in flame retardant formulations.

Algoflon® D 1610 F exhibits good wetting properties and shear stability.

Main features of Algoflon® D 1610 F PTFE dispersion are:

NO polyethoxylated alkylphenols

Very good wetting properties

Good shear stability

Excellent anti-dripping effect

Главная Информация			
Характеристики	Низкий коэффициент трения Хорошая химическая стойкость Теплостойкость, высокая		
Используется	Применение окунания Добавка		
Внешний вид	Белый		
Формы	Латекс		
Физический	Номинальное значение	Единица измерения	Метод испытания
РН	> 9.0		ASTM D4441
Плотность	1.510	g/cm ³	ASTM D4441
Средний размер частиц	250	nm	Internal method
Содержание ПТФЭ-(На смеси)	60.0	wt%	ASTM D4441
Неионный ПАВ-(На смеси)	3.5	wt%	ASTM D4441
Дополнительная информация	Номинальное значение	Единица измерения	Метод испытания

Processing

Algoflon® D 1610 F can be processed undiluted or diluted using distilled or deionized water.

Storage and Handling

Algoflon® PTFE dispersions must be stored under suitable temperature conditions to ensure prolonged stability. Temperatures lower than 5°C must be avoided to prevent irreversible settling. Also, some settling may occur on prolonged standing and/or heat exposure. It is therefore strongly recommended that the product is always kept at temperatures below 35°C. The optimum storage temperature range is 10-25°C. It is also advisable that the product is homogenized by gentle rolling or stirring once per month and prior to use.

Safety and Toxicology

Before using Algoflon® PTFE dispersions consult the product Material Safety Data Sheet and follow all label directions and handling precautions. As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Venting units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes. See Material Safety Data Sheet for detailed advice on waste disposal methods

Packaging

Algoflon® D 1610 F is packaged in either 30 kg drums or 1500 kg IBC's.

Additional Technical Information

For Material Safety Data Sheet or additional technical information consult your Solvay Specialty Polymers sales representative.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

