Escorene™ Ultra FL 02020

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

Описание материалов:

FL 02020 is mainly designed for high speed/low coating extrusion coating, and is a good coextrusion component that can be matched with other polymers. FL 02020 is an excellent heat sealing material with extremely low sealing temperature and high transparency. Good extrusion coating effect can be obtained at 220°C (428 °F) under processing conditions. Processing temperatures above 240°C (464 °F) may cause resin degradation. FL02020 should be put into the extruder after low density polyethylene with similar or higher melt index. The machine should be thoroughly cleaned with low density polyethylene or suitable detergent before stopping.

Главная Информация			
Добавка	Стабилизатор тепла		
Физический	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Содержание винилацетата	20.0	wt%	ExxonMobil Method
Твердость	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Твердость дюрометра (Shore A, 15 sec)	87		ASTM D2240
Механические	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Модуль растяжения [1]	35.0	MPa	ASTM D638
Удлинение при растяжении [2] (Break)	> 100	%	ASTM D638
Тепловой	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Викат Температура размягчения	48.0	°C	ASTM D1525

Юридическое заявление

□□□□□□□□□□□□□,□□□□□□□□□□□□□

WeChat