

## Baytec® U1281XA

Polyurethane Thermoset Elastomer

Covestro - PUR

### Описание материалов:

Baytec U1281XA system is designed for edge molding applications, and forms a tough, durable elastomer that is cut and mar resistant with a hardness of 75 Shore A. As with any product, use of Baytec U1281XA system in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability for use.

| Главная Информация            |  |                 |
|-------------------------------|--|-----------------|
| Формы                         | Жидкость   |                 |
| Твердость                     | Номинальное значение                                       | Метод испытания |
| Твердость дюрометра (Shore A) | 68 - 75  | ASTM D2240      |
| Термокомплект                 | Номинальное значение                                       |                 |
| Компоненты термокомплекта     |  |                 |
| Component a                   | Mixing ratio by weight: 39, mixing ratio by capacity: 1.0  |                 |
| Component B                   | Mixing ratio by weight: 100, mixing ratio by capacity: 3.0 |                 |

| Дополнительная информация  |  |
|--|--|
| Part A   |  |
| Type: Isocyanate   |  |
| Appearance: Dark brown liquid  |  |
| Specific Gravity @ 77°F: 1.23  |  |
| Viscosity @77°F: 135 cps   |  |
| Part B   |  |
| Type: Polyol   |  |
| Appearance: Dark brown liquid  |  |
| Specific Gravity @ 77°F: 1.06  |  |
| Viscosity @77°F: 1300 to 2300 cps  |  |
| Isocyanate Component Temperature: 75 to 95°F Polyol Component Temperature: 75 to 95°F Mold Temperature: 120 to 160°F Demold Time: Up to 10 minutes |  |

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

### Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

