

Bayflex® 5110

Polyurethane

Covestro - PUR

Описание материалов:

Bayflex 5510 is a water-blown polyurethane semi-flexible foam system designed as back-fill support for vinyl extrusion, especially window lineals. This system is capable of filling 16-foot long extrusions, including cavities with small cross sections. As with any product, use of Bayflex 5110 system in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability for use.

Главная Информация	
Используется	Двери и окна Пена
Формы	Жидкость

Дополнительная информация

Part A

Appearance: Dark Brown Liquid

Specific Gravity at 77°F: 1.23

Viscosity at 77°F: 135 cps

Part B

Appearance: Milky White Liquid

Specific Gravity at 77°F: 1.02 to 1.05

Viscosity at 77°F: 1300 to 2000 cps

Hand Mix Reaction Profile at 77°F

Cream Time: 40 to 60 sec

Gel Time: 140 to 170 sec

Free rise Density: 5.5 to 6.6 lb/ft³

Molding Parameters

Isocyanate Component Temperature: 75 to 85°F

Polyol Component Temperature: 85 to 95°F

Cycle Time: 10 min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat