

Shandong PA6 A1RG7301

Стекловолокно

Polyamide 6

Shandong Dongchen Engineering Plastics Co., Ltd.

Описание материалов:

Shandong PA6 A1RG7301 is a Polyamide 6 (Nylon 6) material filled with glass fiber. It is available in Asia Pacific.

Important attributes of Shandong PA6 A1RG7301 are:

Flame Rated

Heat Resistant

High Strength

Wear Resistant

Typical applications include:

Appliances

Automotive

Electrical/Electronic Applications

Главная Информация	
Наполнитель/армирование	Стекловолокно
Характеристики	Хорошая износостойкость
	Высокая термостойкость
	Высокая прочность
Используется	Приборы
	Автомобильные Приложения
	Электрическое/электронное применение

Механические	Номинальное значение	Единица измерения
Tensile Stress (Yield)	145	MPa
Растяжимое напряжение (Break)	3.0	%
Флекторный модуль	8500	MPa
Флекторный стресс	200	MPa

Воздействие	Номинальное значение	Единица измерения
Ударная прочность	25	kJ/m ²
Charpy Unnotched Impact Strength	100	kJ/m ²

Воспламеняемость	Номинальное значение	Метод испытания
Огнестойкость	HB	UL 94

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

