

Flextuff® S2800-00

Thermoplastic Elastomer

Noble Polymers

Описание материалов:

80 Shore A TPE

Noble Polymers Flextuff series of Thermoplastic Elastomer Compounds (TPE) offer rubber-like feel with the ease of processing and recyclability of a thermoplastic. This unique family of products are developed using the highest quality raw materials and additives to create soft feel materials in a wide range of hardness levels for both injection molding as well as extrusion processing methods.

Flextuff TPE compounds are used in applications such as grips, seals, over-molded handles and many other applications in the commercial, automotive, sports and leisure and building and construction industries.

Features Include:

Durometer (hardness) range from 25 - 90 Shore A

Available in natural, black or custom colors

Additive packages include: UV stabilization, scratch and mar resistance

Formulations for injection molding as well as profile extrusion

Customized formulations available to meet your specific need

All Flextuff products are 100% recyclable

| Главная Информация | | | |
|---|-------------------------------------|-------------------|-----------------|
| Характеристики | Перерабатываемый материал | | |
| Используется | Автомобильные Приложения | | |
| | Применение конструкции | | |
| | Гибкие ручки | | |
| | Ручки | | |
| | Уплотнения | | |
| Внешний вид | Спортивные товары | | |
| | Черный | | |
| | Доступные цвета Натуральный цвет | | |
| Метод обработки | Литье под давлением | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Удельный вес | 0.920 | g/cm ³ | ASTM D792 |
| Массовый расход расплава (MFR) (230°C/2.16 kg) | 11 | g/10 min | ASTM D1238 |
| Твердость | Номинальное значение | Единица измерения | Метод испытания |
| Твердость дюрометра (Shore A) | 80 | | ASTM D2240 |
| Эластомеры | Номинальное значение | Единица измерения | Метод испытания |
| Прочность на растяжение | 7.76 | MPa | ASTM D412 |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

