

NatureFlex™ 110NP

Regenerated Cellulose

Innovia Films Ltd.

Описание материалов:

NatureFlex films are manufactured from renewable wood pulp harvested from plantations operating good forestry management principles. Heat-sealability and barrier properties are achieved through Innovia Films' proprietary coating technologies.

Literature reference: N200

Transparent, non-heat sealable film for applications such as bagmaking and where moisture barrier is not required

Главная Информация			
Характеристики	Биоразлагаемый Compostable Высокая четкость Содержание возобновляемых ресурсов		
Используется	Пленка Упаковка		
Внешний вид	Прозрачный/прозрачный		
Формы	Пленка		
Пленки	Номинальное значение	Единица измерения	Метод испытания
Скорость передачи кислорода (влажная) ¹ (24°C, 28 µm, 0.0% RH)	3.10	cm ³ /m ² /24 hr	ASTM F1927
Передача водяного пара ²	1500	g/m ² /24 hr	ASTM E96
Датчик пленки	27.7	µm	Internal Method
Выход (27.7 µm)	25.0	m ² /kg	Internal Method
Оптимальная ширина декорации	142.24	cm	
NOTE			
1.	RH: 0 to 5%		
2.	100°F, 90%RH		

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

