

ELASTOSIL® E 14

Silicone

Wacker Chemie AG

Описание материалов:

Silicone Rubber, RTV-1

Wet-Type Gaskets, Automotive & Transportation

Bonding & Sealing, Adhesives and Sealants

Small Appliances, Household Appliances

Heating and Air Conditioning, Household Appliances

Heating and Air Conditioning, Mechanical and Plant Engineering

Bonding & Sealing, Mechanical and Plant Engineering

Главная Информация

Используется	Клеи
	Склеивание
	Герметики

Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Red		
Плотность			
--	1.15	g/cm ³	DIN 53479
--	1.18	g/cm ³	ISO 1183
Время отверждения	12	hr	
Skin Forming Time ¹ (23°C)	15.0 to 20.0	min	

Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суху (Shore A)	38		DIN 53505
Прочность на растяжение	3.00	MPa	DIN 53504
Удлинение при разрыве	450	%	DIN 53504
Tear Strength	7.00	kN/m	ASTM D624B

NOTE

1. 50% R.H

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

