

## Deco-Coat™ UV Cure 7156™

Epoxy; Epoxide

Epoxies, Etc.

### Описание материалов:

UV Cure 7155™ and 7156™ are low intensity UV Curable Epoxy Resins. These products are water clear and cure to a smooth, bubble free finish. Low cost, low intensity lights are all that is needed to cure these unique polymer systems. UV Cure 7155™ and 7156™ also have superior aging and yellowing resistance.

#### Applications:

UV Cure 7155™ and 7156™ may be used as decorative ultra clear doming resins on labels, pins, key fobs, magnets, ceramics, etc... UV Cure 7155™ and 7156™ have outstanding adhesion to photographic paper. Their high gloss finish and outstanding clarity will enhance any image it is applied over. These materials can also be used as protective coatings due to their ability to resist moisture, chemicals and thermal shock.

#### Benefits:

No weighing or mixing

Single component

Cures in minutes

Non-solvent 100% solids system

Can be cured with low intensity black light

### Главная Информация

Характеристики	Хорошая адгезия	
	Хорошая химическая стойкость	
	Хорошая гибкость	
	Хорошая термостойкость	
	Высокая четкость	
	Глянцевый	
	Влагостойкий	
	УФ изгибаемый	
Используется	Нанесение покрытия	
	Декоративные детали	
	Этикетки	
Внешний вид	Прозрачный/прозрачный	
Uncured Properties	Номинальное значение	Единица измерения
Цвет	Clear/Transparent	
Содержание твердых веществ	100	%
Плотность (25°C)	1.09	g/cm <sup>3</sup>
Вязкость (25°C)	1.0	Pa·s
Срок годности (4°C)	6	month
Cured Properties	Номинальное значение	Единица измерения
Твердость по суше (Shore A)	95	
Прочность на растяжение	60.7	MPa

Удлинение при разрыве	6.1	%
Относительная проницаемость (60 Hz)	3.16	
Сопrotивление громкости	1.6E+9	ohms-cm
Коэффициент рассеивания (60 Hz)	0.018	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat