

Formolon® 10

Polyvinyl Chloride Homopolymer

Formosa Plastics Corporation, U.S.A.

Описание материалов:

F-10 is a medium molecular weight PVC homopolymer dispersion resin with low residual surfactant content. Plastisol prepared using F-10 exhibit low paste viscosity as well as excellent clarity and heat stability. Applications include sheet goods flooring wearlayer, low density chemical blow foam and strand coating.

| Главная Информация | | |
|-------------------------------|--|-----------------|
| Характеристики | Диспергируемый Хорошая термическая стабильность Высокая четкость Гомополимер Низкие размеры Низкая вязкость Средний Молекулярный вес | |
| Используется | Нанесение покрытия Напольное покрытие Пена | |
| Рейтинг агентства | EC 1907/2006 (REACH) | |
| Формы | Гранулы | |
| Физический | Номинальное значение | Метод испытания |
| K-Value | 68.0 | |
| Внутренняя вязкость | 0.98 | ASTM D1243 |
| Relative Viscosity | 2.30 | |
| Вязкость брукфилда | | |
| -- 1 | 4.50 | Pa·s |
| -- 2 | 6.00 | Pa·s |
| Вязкость Портера ³ | 8.00 | Pa·s |
| Температура геля | 70 | °C |
| Добыча метанола | 1.5 | % ASTM D2222 |
| Испарители | 0.30 | % ASTM D3030 |
| NOTE | | |
| 1. | 20 rpm, aged 2 hr | |
| 2. | 2 rpm, aged 2 hr | |
| 3. | 100 psig, aged 2 hr | |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

