

## Shida 3310

Thermoplastic Elastomer

JINJIANG City SHIDA Plastic Fine Co., Ltd.

### Описание материалов:

Our TPE can enhance the elasticity and tenderness of products such as EVA, PE, SBS, PS, and PP during the processing. With good compatibility with EVA, it can reduce the hardness of the materials and make them more flexible and tender, EVA shooting out slippers and flat forming in particular. Hence, it upgrades shoes' rank.

Главная Информация			
Используется	Пластиковая модификация		
Формы	Частицы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.18	g/cm <sup>3</sup>	ISO 1183
Массовый расход расплава (MFR) (180°C/5.0 kg)	4.5	g/10 min	ISO 1133
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	28		ISO 868
Механические	Номинальное значение	Единица измерения	Метод испытания
Tensile Stress	9.00	MPa	ISO 527-2
Растяжимое напряжение (Break)	700	%	ISO 527-2
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Tear Strength	58	kN/m	ISO 34-1

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat