

LUVOCOM® 3-7901

Стекловолокно

Polyamide 6

Lehmann & Voss & Co.

Описание материалов:

LUVOCOM®3-7901 is a polyamide 6 (nylon 6) material, which contains glass and carbon fiber reinforced materials. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 3-7901 are:

Conductivity

Electrostatic protection

Good stiffness

Wear-resistant

Typical application areas include:

engineering/industrial accessories

House

textile/fiber

Automotive Industry

Handle

Главная Информация			
Наполнитель/армирование	Армированные материалы из стекла и углеродного волокна		
Характеристики	<p>Проводящий</p> <p>Жесткий, хороший</p> <p>Защита от электростатического разряда</p> <p>Хорошая прочность</p> <p>Хорошая стойкость к стиранию</p>		
Используется	<p>Ручка</p> <p>Текстильные изделия</p> <p>Инженерные аксессуары</p> <p>Ролик</p> <p>Применение в автомобильной области</p> <p>Чехол</p>		
Внешний вид	Синий		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.44	g/cm ³	ISO 1183
Формовочная усадка	0.10 - 0.50	%	DIN 16901
Поглощение воды (23°C, 24 hr)	< 1.0	%	
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения	14000	MPa	ISO 527-2
Tensile Stress (Break)	165	MPa	ISO 527-2

Растяжимое напряжение (Yield)	2.2	%	ISO 527-2
Флекторный модуль	24000	MPa	ISO 178
Флекторный стресс	230	MPa	ISO 178
Flexural Strain at Flexural Strength	2.5	%	ISO 178
Максимальная рабочая температура-Короткий срок	130	°C	
Insulation Resistance	1.0E+4	ohms	IEC 60167
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Charpy Unnotched Impact Strength (23°C)	43	kJ/m ²	ISO 179/1eU
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура непрерывного использования	110	°C	UL 746B
Инъекция	Номинальное значение	Единица измерения	
Температура сушки			
A	75.0	°C	
B	105	°C	
Время сушки			
A	10 - 16	hr	
B	4.0 - 6.0	hr	
Рекомендуемая максимальная влажность	0.10	%	
Задняя температура	250 - 270	°C	
Средняя температура	270 - 290	°C	
Передняя температура	280 - 300	°C	
Температура сопла	270 - 280	°C	
Температура обработки (расплава)	270	°C	
Температура формы	70.0 - 110	°C	
Инструкции по впрыску			

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing the moisture level should not exceed 0.1%, otherwise molecular degradation and surface defects (e.g. smearing) may occur. As the material absorbs water rapidly, originally sealed containers should only be opened immediately before processing. Excessively high predrying temperatures may cause discoloration.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat