

# Hifax ETA3041 YGYA BLK

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

## Описание материалов:

Hifax ETA3041 YGYA BLK medium melt flow, 170 MPa flexural modulus, thermoplastic elastomeric olefin (TEO) resin has a good balance of flexibility and durability. It is typically used for a wide variety of molded-in color automotive exterior components.

For regulatory compliance information, see Hifax ETA3041 YGYA BLK Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Главная Информация			
Характеристики	Хорошая гибкость Средняя степень жидкости Долговечность		
Используется	Применение в автомобильной области		
Метод обработки	Литье под давлением		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность (23°C)	0.900	g/cm <sup>3</sup>	ISO 1183
Массовый расход расплава (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Механические	Номинальное значение	Единица измерения	Метод испытания
Tensile Stress (Yield)	7.00	MPa	ISO 527-2
Флекторный модуль	170	MPa	ISO 178

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat