

Petrothene® GA625662

Linear Low Density Polyethylene

LyondellBasell Industries

Описание материалов:

Petrothene GA625662, a hexene LLDPE, pelletized rotational molding resin with excellent flow properties, can be used to produce a variety of objects such as toys, playground equipment, drums and agricultural and chemical storage containers. GA625662 exhibits excellent ESCR, low temperature impact strength and warp resistance. It is UV-stabilized and available in a 35-mesh powder as Microthene MP625662.

Главная Информация		
Добавка	УФ-стабилизатор	
Характеристики	Высокий уровень ЭСКП (устойчивость к растрескиванию)	
	Гексен-комномер	
	Сопротивление изгибу	
	Хорошая мобильность	
Ударопрочность при низкой температуре		
Используется	Барабан	
	Сельскохозяйственное применение	
	Контейнер	
	Спортивные товары	
Игрушка		
Формы	Частицы	
Метод обработки	Ротационное формование	
Физический	Номинальное значение	Единица измерения
Плотность (23°C)	0.935	g/cm ³
Массовый расход расплава (MFR) (190°C/2.16 kg)	5.0	g/10 min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

