

VICOTE® F808 Natural

Polyetheretherketone

Victrix plc

Описание материалов:

The VICOTE F808 natural, F809 natural and F810Blk grades have been specifically formulated to provide a resilient coating with high wear and abrasion resistance combined with excellent release properties on ferrous substrates such as carbon and cast steels. These properties are retained at high temperatures where other release coatings would potentially fail. VICOTE dispersions have a low level of extractables. Contact Victrix for further details.

VICOTE F808 natural, F809 natural and F810Blk dispersions are aqueous based however there are small amounts of solvents present. Refer to the appropriate MSDS sheet for details.

The VICTREX® PEEK polymer contained in the VICOTE dispersions like other non-coating grades of VICTREX PEEK polymer are thermoplastic in nature and exhibit flow above the melt temperature. When processed using the correct guidelines the coatings will exhibit the excellent properties that VICTREX PEEK polymer is renowned for.

VICOTE products have excellent chemical resistance. Consult the Victrix Chemical Resistance Data brochure for further details.

Главная Информация			
Характеристики	Хорошая стойкость к истиранию Хорошая химическая стойкость Хорошая износостойкость Высокая термостойкость Низкий уровень извлечения Упругий		
Используется	Нанесение покрытия		
Рейтинг агентства	Управление по санитарному надзору за качеством пищевых продуктов и медикаментов 21 CFR 175,300		
Внешний вид	Натуральный цвет		
Формы	Жидкость		
Метод обработки	Покрытие Распыление		
Механические	Номинальное значение	Метод испытания	
Коэффициент трения ¹	0.10	ASTM G133	
Дополнительная информация	Номинальное значение	Единица измерения	Метод испытания
Сцепление поперечного люка ²			ISO 2409
Aluminum	0		
Mild Steel	0		
Stainless Steel	0		
Прямое воздействие ³			ISO 6272
Height	100.00	cm	
Indentation depth	0.50	cm	
Weight	2000	g	

Твердость König (от 40,0 до 50,0 мкм)	2.8	min	ISO 1522
---------------------------------------	-----	-----	----------

NOTE

1. Using 250N Load, μm @ 10 min
2. Rating 0 to 5
3. Part 1

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat